

TECHNICAL DATA SHEET

Silzot® FS-X1

Description: Silzot® FS-X1 injection moulding feedstock (with 15-20% polymers and sintering additives) for production of sintered silicon nitride ceramics.

Chemical

Characteristics: (after debinding)	α - Si_3N_4	min. 86 %
	O- content	max. 6.0 %
	C- content	max. 0.2 %
	Fe- content	max. 0.1 %
	Ca- content	max. 0.03 %

Physical

Characteristics:

Inorganic

Components: SSA min. 11 m²/g

Organic

Components: Mould Temp. 150-160°C

Alzchem Trostberg GmbH, Dr. Albert-Frank-Straße 32, 83308 Trostberg

Contact:

Maciej Kuczynski
Phone +49 8621 86-3022, Fax +49 8621 86-503022
maciej.kuczynski@alzchem.com / finechemicals@alzchem.com

This information and all technical and other advice are based on Alzchem's present knowledge and experience. However, Alzchem assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights or to laws and provisions. Alzchem reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. ALZCHEM DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF ALZCHEM IS AWARE OF SUCH PURPOSE), OR OTHERWISE. ALZCHEM SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of incoming products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Edition: 01/2022 (This data sheet supersedes all previous data sheets for this product)